



HEMPADUR FAST DRY 17410

17410: BASE 17419: CURING AGENT 98410

Description:

HEMPADUR FAST DRY 17410 is a two-component, high build epoxy paint which combines a relatively high volume solids content with a short drying time. Contains zinc phosphate.

Recommended use:

As a primer in mild to medium atmospheric environments.
As an intermediate or finishing coat in epoxy systems in medium to severely corrosive atmospheric environments.
As a finishing coat only where yellowing and chalking are acceptable.

Service temperature:

Maximum, dry exposure only: 140°C/284°F

Certificates/Approvals:**Availability:**

Part of Group Assortment. Local availability subject to confirmation.

PHYSICAL CONSTANTS:

Shade nos/Colours: 11480* / Grey.
Finish: Semi-gloss
Volume solids, %: 74 ± 1
Theoretical spreading rate: 7.4 m²/l [296.7 sq.ft./US gallon] - 100 micron/4 mils
Flash point: 26 °C [78.8 °F]
Specific gravity: 1.5 kg/litre [12.9 lbs/US gallon]
Dry to touch: 1.5 approx. hour(s) 20°C/68°F
Fully cured: 7 day(s) 20°C/68°F
VOC content: 273 g/l [2.3 lbs/US gallon]

**other shades according to assortment list.*

The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.

APPLICATION DETAILS:**Version, mixed product:**

17410

Mixing ratio:

BASE 17419: CURING AGENT 98410

4 : 1 by volume

Thinner (max.vol.):

HEMPEL'S THINNER 08450 <5% depending on purpose (see REMARKS overleaf)

Pot life:

1.5 hour(s) 20°C/68°F

Nozzle orifice:

0.019 - 0.021 "

Nozzle pressure:

225 bar [3262.5 psi]
(Airless spray data are indicative and subject to adjustment)

Cleaning of tools:

HEMPEL'S TOOL CLEANER 99610

Indicated film thickness, dry:

100 micron [4 mils] (see REMARKS overleaf)

Indicated film thickness, wet:

135 micron [5.4 mils]

Recoat interval, min:

According to specification.

Recoat interval, max:

According to specification.

Safety:

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.



HEMPADUR FAST DRY 17410

SURFACE PREPARATION:

New steel: Abrasive blasting to Sa 2½ (ISO 8501-1:2007). For temporary protection, if required, use a suitable shopprimer. All damage of shopprimer and contamination from storage and fabrication should be thoroughly cleaned prior to final painting. For repair and touch-up use: HEMPADUR FAST DRY 17410.

Maintenance: Remove oil and grease etc. thoroughly with suitable detergent. Remove salts and other contaminants by high pressure fresh water cleaning. Remove all rust and loose material by wet or dry abrasive blasting or power tool cleaning. Feather edges to sound and intact areas. Dust off residues. Touch up to full film thickness. After wet abrasive blasting hose down the surface with fresh water and allow drying.

APPLICATION CONDITIONS:

Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. Use only where application and curing can proceed at temperatures above: -10°C/14°F.

The temperature of the paint itself should be: 15-25°C/59-77°F.

In confined spaces provide adequate ventilation during application and drying. Thinning may be necessary in the case of very long spray hoses and/or paint temperatures below: 15°C/59°F. This will cause lower film build and longer drying time.

PRECEDING COAT

According to specification. Recommended systems are: Spray metallisation, HEMPADUR ZINC 17360, HEMPEL'S GALVOSIL 15700.

It is important that the surface is completely clean to ensure the adhesion. Any oil, grease, etc. to be removed by suitable detergent.

SUBSEQUENT COAT:

None, or as per specification. Recommended systems are: HEMPATHANE, HEMPADUR, HEMPAXANE.

REMARKS:

Colours/Colour stability:

Has a tendency to yellow after application. This has no influence on the performance nor does the yellowing affect any topcoat applied.

Weathering/service temperatures:

The natural tendency of epoxy coatings to chalk in outdoor exposure and to become more sensitive to mechanical damage and chemical exposure at elevated temperatures is also reflected in this product.

Application(s)

Irregular surfaces: Special care should be taken in relation to irregular surfaces (welding seams, undercuts etc.) as application with an excessive film thickness may result in cracking especially on such areas. Excessive film thickness per coat is typically more than: 300 micron/12 mils.

Application onto zinc metallized and zinc silicate primed surfaces: Can be used on top of Zinc silicate or on metallised area by use of the flash coat technique.

Depending on actual conditions of application, such as temperature, porosity of substrate, method of spray, a sealer coat (thinned up to 30%) can be applied as an alternative method to reduce popping, followed by application of the full coat.

Film thicknesses/thinning:

May be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate and may influence drying time and recoating interval. Normal range dry is: 80-125 micron/3.2-5 mils.

Selection of proper thinner is related to application conditions. Recommended systems are: HEMPEL'S THINNER 08450. HEMPEL'S THINNER 08700 may be used alternatively depending on local conditions.

Recoating note:

In case of general maintenance involving epoxy systems of high total dry film thickness, the minimum recoating interval may advantageously be doubled up.

For mild atmospheric exposure recoating with HEMPADUR and HEMPATHANE qualities has no maximum. For other qualities please contact HEMPEL.

A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals. Any dirt, oil, grease, and other foreign matter must be removed with suitable detergent followed by (high pressure) fresh water cleaning. Salts to be removed with by fresh water hosing.

Any degraded surface layer, as a result of a long exposure period, must be removed as well.

Note:

HEMPADUR FAST DRY 17410 For professional use only.

ISSUED BY:

HEMPEL A/S

1741011480

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.